

PRODUCT DATA SHEET

Sika Waterbar® A AT

Internal waterbars for construction joints

DESCRIPTION

Sika Waterbar® A AT are flexible, internal waterbars for construction joints made from PVC-P.

USES

Watertight construction joint sealing in new concrete structures.

Typical structures include for example:

- Residential building basements
- Commercial building basements
- Underground car parks
- Water retaining structures

FEATURES

- Permanent flexibility
- Homogeneous waterbar
- Suitable for low to medium levels of hydrostatic water pressure
- Resistant to all natural mediums in soil and groundwater
- Robust products designed for handling and installation on site
- Suitable for thermal welding on site
- Suitable for welding with recycled PVC-R based Sika Waterbars®

PRODUCT INFORMATION

Composition	PVC-P (plasticized)	
Packaging	Type	Roll length [m]
	SikaWaterbar® A-19	30
	SikaWaterbar® A-24	30
	SikaWaterbar® A-32	15

Shelf life Up to 60 months from date of production.

Storage conditions Store in originally sealed, undamaged packaging, in a dry place at temperatures between +5°C and +30°C.

Long-term storage ≥ 6 months:

- The storage area must be covered, cool, dry, free from dust and moderately ventilated.
- The waterbars must be protected from heat and UV radiation.

Short-term storage < 6 months (on construction sites, outdoors < 6 weeks):

- In dry conditions, protected from UV radiation, snow and ice, and any kind of contamination or mechanical damage.
- Store separately from any potentially harmful or damaging materials, plant or equipment such as structural steel, steel reinforcement, fuel or vehicles, etc.
- Store away from trafficked areas and roads on site to avoid damage.

Appearance and colour	Yellow	
Thickness	Type	Thickness [mm]
	SikaWaterbar® A-19	3.5
	SikaWaterbar® A-24	3.5
	SikaWaterbar® A-32	4.5

SYSTEM INFORMATION

System structure	Suitable for welding with all other PVC-P based Sika Waterbar® types. Suitable for welding with recycled PVC-R based Sika Waterbar® types. Waterbar fixing clips: Clip Type 1 Fixing of SikaFuko® injection hoses: Circlips
-------------------------	--

TECHNICAL INFORMATION

Shore A hardness	75 ± 5	(DIN 53505)
Tensile strength	> 12 MPa	(EN ISO 527-1/-2)
Elongation	> 300 %	(EN ISO 527-1/-2)
Tear strength	> 12 N/mm	(ISO 34-1)
Ambient maximum temperature of liquids	Pressurised water	-20°C min. / +40°C max.
	Non-pressurised water	-20°C min. / +60°C max.
Chemical resistance	Permanent resistant at +23°C: water, seawater, alcalic water and wastewater, deicing salt solutions. Temporarily resistant against: diluted anorganic alcalies and mineral acids, mineral oils. PCV-P waterbars are not compatible with bitumen.	

APPLICATION INFORMATION

Ambient air temperature	+5°C min. / +35°C max.
--------------------------------	------------------------

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- PCV-P waterbars are not compatible with bitumen.
- The quality of the joint sealing depends on the fully enclosure of the waterbar with concrete. In order to obtain a qualitative embedding, gravel nests have to be avoided.
- For a watertight building, attention must be paid to a closed waterbar-system.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above

APPLICATION INSTRUCTIONS

APPLICATION METHOD / TOOLS

Application:

Install the waterbar in the center of the concrete structure. It should be carefully fixed in the formwork before concreting. The waterbar fixing clips shall be installed at maximum 25 cm centres and fixed to the steel reinforcement.

Welding:

The specific welding parameters must be adjusted and checked on samples prior to the welding work. A minimum ambient temperature of +5 °C and dry weather conditions are required for welding on-site.

Sika Waterbar® A AT can be connected by butt welding with suitable welding equipment. The welding edges are melted in the process and fused permanently together whilst in the plastic state.

Protection of exposed waterbars on site:

The waterbars should be protected from damage until they are fully embedded into the concrete.

The waterbar and the joint must be cleaned before concreting.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA ABYSSINIA

Chemicals Manufacturing PLC
Sebeta, Welete · Addis Ababa
ETHIOPIA
Phone: +251.113.679.748
Web: eth.sika.com

PRODUCT DATA SHEET

Sika Waterbar® A AT
February 2024, Version 01.01
020703100100000156

SikaWaterbarAAT-en-ET-(02-2024)-1-1.pdf