

**BUILDING TRUST** 

# PRODUCT DATA SHEET

# SikaCeram<sup>®</sup>-105

General Purpose, Cementitious Tile Adhesive.

## DESCRIPTION

SikaCeram<sup>®</sup>-105 is a cementitious tile adhesive used for permanent fixing of tiles. Suitable for tropical and hot climatic conditions Performance is in accordance with European EN12004: Classification- C1T class

## USES

Suitable for fixing:

- Wall and floor tiles.
- Absorbing / non-absorbed tiles.
- Interior use only.

## **PRODUCT INFORMATION**

## **FEATURES**

- Easy to use, just add water.
- Excellent workability.
- Excellent pot life.
- Can be applied directly on cement screeds, concrete or lime mortars.
- Non Toxic.
- Suitable for indoor application.

Composition	Cementitious powder, Polymer modified binder. 25 kg bag 12 months minimum from production date if stored properly in original unopened, sealed and undamaged packaging.	
Packaging		
Shelf life		
Storage conditions	Store in a dry area between 5°C and 35 ℃. Protect from direct sunlight.	
Appearance and colour	Grey Powder	

### **TECHNICAL INFORMATION**

Tensile adhesion strength	≥ 0.5 MPa	

## APPLICATION INFORMATION

Mixing ratio	<ul> <li>26% - 28% (6.5kg - 7.0kg) of water for 25kg product</li> <li>The consumption is 3 – 6 kg/m<sup>2</sup> depending on <ul> <li>the substrate (flatness, roughness)</li> <li>the tiles type (size, thickness, water absorption, porosity)</li> <li>gluing method (simple or double)</li> </ul> </li> </ul>	
Consumption		
Ambient air temperature	Minimum 5°C, Maximum 30°C (Substrate).	

PRODUCT DATA SHEET SikaCeram®-105 June 2023, Version 01.01 021710102000000050 Open Time

~ 20 minutes at room temperature

## **BASIS OF PRODUCT DATA**

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

# IMPORTANT CONSIDERATIONS

All technical data stated in this Product Data Sheet are based on laboratory tests.

Actual measured data may vary due to circumstances beyond our control.

Remark:

 SikaCeram<sup>®</sup>-105 should not be used directly on gypsum or gypsum board substances. Contact our Technical Service Department for advice.

# ECOLOGY, HEALTH AND SAFETY

For any information regarding safety issues in the use, handling, storage and disposal of chemical products, users should refer to the latest version of the Data Sheet Product Safety containing physical, ecological, toxicological data and other security issues.

# **APPLICATION INSTRUCTIONS**

#### SUBSTRATE QUALITY / PRE-TREATMENT

Concrete, mortar and masonry surfaces must be clean, free from grease, oil and loosely adhering particles. Suitable mechanical methods such as abrasive blast cleaning; high pressure water jetting at sufficient pressure (minimum 150 bars) and volume; scabbling or needle gunning. On "new" or smooth faced concrete, surfaces as should be Sand-blasted. All surfaces must be as true and flat as possible. Blow holes and irregularities should be filled with suitable SikaTop / Monotop products. Saturate absorbent concrete surfaces thoroughly with water to achieve a surface saturated dry (SSD) condition.

#### MIXING

Add about 6.5 – 7.0 litres clean water to a clean suitable mixing container. Slowly add the SikaCeram®-105 powder and mix for at least 3 minutes until a homogeneous mix free of lumps is achieved. Do not mix more SikaCeram®-105 than can be used within the open time. Do not add extra water or other ingredients after mixing!

#### SIKA ABYSSINIA

Chemicals Manufacturing PLC Sebeta, Welete · Addis Ababa ETHIOPIA Phone: +251.113.679.748 Web: eth.sika.com

#### APPLICATION

Apply SikaCeram<sup>®</sup>-105 at 3 -10 mm thickness directly to the concrete substrate, using a notched trowel and spread the mortar evenly over the area to be tiled. Cover only an area that can be tiled within 15 - 20 minutes. Press tiles firmly into SikaCeram<sup>®</sup>-105 with a twisting action to ensure optimum adhesion.

- 1. Use 6.5 7.0 litres of clean water per 25kg bag.
- 2. Mix well with a slow speed drill (maximum 500rpm).
- 3. Apply with "V"-notched trowels for small tiles.
- 4. Apply with square notched trowel for bigger tiles.
- 5. Place the tiles firmly into the fresh adhesive.

#### **CLEANING OF EQUIPMENT**

Application and mixing tools should be cleaned with water while material is still fresh. Hardened material can only be removed mechanically.

# LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

# **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



SikaCeram-105-en-ET-(06-2023)-1-1.pdf

PRODUCT DATA SHEET SikaCeram®-105 June 2023, Version 01.01 021710102000000050

**BUILDING TRUST**