

# PRODUCT DATA SHEET

## SikaSeal®-105

### Multi-Purpose Waterproofing Slurry

#### DESCRIPTION

SikaSeal®-105 is a cement based, polymer modified, 2-component, multipurpose waterproofing slurry. SikaSeal®-105 is cementitious waterproof coating system with the excellent waterproofing ability of special polymers, fillers, and properly graded aggregates.

#### USES

SikaSeal®-105 is used as an economical and easy to use waterproofing slurry both for external and internal applications. SikaSeal®-105 is suitable for the following applications:

- Water & sewage works, such as tanks and manholes
- Basements and lift pits

- Retaining walls and bridge structures
- Sea walls and irrigation channels
- Balconies, bathrooms etc.

SikaSeal®-105 can be used against positive and negative water pressure.

#### FEATURES

SikaSeal®-105 is part of a complete Sika System for the economical water proofing of water containment structures. SikaSeal®-105 offers following advantages:

- Pre-batched components (no water added).
- Impermeable
- Brush, trowel or spray applied.
- Good adhesion to sound substrates
- Non-Toxic

#### PRODUCT INFORMATION

<b>Composition</b>	Cement, selected graded aggregates and polymer dispersion.		
<b>Packaging</b>	25 kg units (5 kg pails of component A and 20 kg bags of component B)		
<b>Shelf life</b>	12 months minimum from production date		
<b>Storage conditions</b>	Store in a dry area in original sealed packaging between 5 °C and 35 °C. Protect from direct sunlight.		
<b>Appearance and colour</b>	Component A: White liquid Component B: Grey powder		
<b>Maximum grain size</b>	~0.5 mm		
<b>Density</b>	~2.00 kg/lit (fresh mortar)		
<b>Compressive strength</b>	<b>7 Days</b> > 20 MPa	<b>28 Days</b> > 30 MPa	UNE EN 1015-11
<b>Tensile strength in flexure</b>	<b>7 Days</b> > 5 MPa	<b>28 Days</b> > 8 MPa	UNE EN 1015-11
<b>Tensile adhesion strength</b>	≥ 1 MPa		UNE EN 1542

## APPLICATION INFORMATION

<b>Mixing ratio</b>	Used as slurry, A : B	1 : 4 by weight
	Used as mortar, A : B	1 : 4.5 by weight
<b>Consumption</b>	2.0 kg/m <sup>2</sup> minimum / 4.0 kg/m <sup>2</sup> maximum. Consumption depends on substrate roughness, surface profile, wastage etc. For water retaining structures, use total of 4.0 – 8.0 kg/m <sup>2</sup> of SikaSeal®-105 depending on water head. Apply a minimum of two coats. For damp proofing, use a minimum of 2.0 kg/m <sup>2</sup> .	
<b>Layer thickness</b>	1 mm min. / 2 mm max. per coat	
<b>Ambient air temperature</b>	+5 °C min. / +40 °C max.	
<b>Substrate temperature</b>	+5 °C min. / +40 °C max.	
<b>Pot Life</b>	~ 30 min.	
<b>Waiting time to overcoating</b>	Waiting time between coats:	
	+10°C	~12 hours
	+20°C	~6 hours
	+30°C	~3 hours
	If waiting time period exceeds 24 hours, lightly blastclean the surface. SikaSeal®-105 can be over-painted using solvent based primers or coatings. SikaSeal®-105 must cure for a minimum of 7 days before over-coating.	

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

Avoid application in direct sun and/or strong wind. Protect from rain and other forms of moisture and liquids until cured as 'bloomings' might result. SikaSeal®-105 is not designed as an aesthetic coating. Do not add water under any circumstances. Apply only to sound, prepared, pre-dampened substrates

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY / PRE-TREATMENT

Surfaces must be clean, sound, free from grease, oil and loosely adhering particles. The substrate must have a pull-off strength (tensile

adhesive) of at least 1.0 N/mm<sup>2</sup>.

Use suitable mechanical methods such as abrasive blast cleaning, high pressure water jetting (minimum 150 bar), scabbling or needle gunning. New or smooth faced concrete surfaces should be sandblasted. All surfaces must be as true and flat as possible. Blowholes and irregularities should be filled with suitable SikaTop® / Sika MonoTop® products. Saturate absorbent concrete surfaces thoroughly with water to achieve a surface saturated dry condition.

### MIXING

Stir component A (liquid) thoroughly before pouring into a clean mixing container. Add component B (powder) slowly while mixing continuously. Use forced action mixers or low speed electric mixers (maximum 500 rpm) with basket type mixing blades for 3 minutes avoiding entrapment of air. By adding the powder in portions, the desired application consistency can be obtained. For a trowelable consistency use about 90 % of component A approximately 4.5 kg).

### APPLICATION

While the substrate is still in a saturated surface dry condition, apply the first coat by notched trowel and leave to harden. Apply the second coat as soon as possible, after hardening of the first coat, to ensure proper adhesion between layers.

**Slurry:** Apply by spray or with a hard bristle brush or broom. Apply second coat at right angle to the first.

#### PRODUCT DATA SHEET

SikaSeal®-105

June 2023, Version 01.01  
020701010020000026

**Mortar:** For the trowelable mortar use a notched trowel for the first coat. Apply the second coat into the notches and smoothen the surface. For floor applications, to avoid risk of damage to the first coat, it is recommended to apply the second coat after 24 hours. In such cases, the first coat should be slightly re-wetted. After application of the second coat, finish SikaSeal®-105 by rubbing down with a soft dry sponge.

**Spray:** The product can also be sprayed with a suitable mortar pump. For example Wagner PlastCoast 830 spraypack and a 4 mm nozzle. Refer to Sika's Technical Department for further advice.  
In case of a third coat, scratch the surface of the second coat with the edge of the trowel to provide a mechanical key.  
For further information please consult our Technical Department.

### **CURING TREATMENT**

Protect from rapid drying by applying an Antisol curing compound or protecting with polythene sheeting.

### **CLEANING OF EQUIPMENT**

Clean all tools and equipment with clean water immediately after use.  
Hardened / cured material can only be removed mechanically

## **LOCAL RESTRICTIONS**

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### **SIKA ABYSSINIA**

Chemicals Manufacturing PLC  
Sebeta, Welete · Addis Ababa  
ETHIOPIA  
Phone: +251.113.679.748  
Web: eth.sika.com

#### **PRODUCT DATA SHEET**

SikaSeal®-105  
June 2023, Version 01.01  
020701010020000026