

## PRODUCT DATA SHEET

# Sikagard®-6220 S

Sprayable, high penetrating cavity wax in aerosol can

**TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)**

Chemical base	Wax solution	
Color (CQP001-1)	Amber	
Cure mechanism	Air-drying	
Density (uncured)	0.66 kg/l	
Solid content (CQP002-1)	30 %	
Application temperature	15 – 75 °C	
Film thickness	wet	100 µm
	dry	30 µm
Drying time	2 h <sup>A</sup>	
Service temperature	-50 – 75 °C	
Shelf life	24 month <sup>B</sup>	

CQP = Corporate Quality Procedure

<sup>A</sup>) 23 °C / 50 % r. h.<sup>B</sup>) storage between 5 °C and 25 °C
**DESCRIPTION**

Sikagard®-6220 S is an amber colored, easy to use, durable wax in an aerosol can with very good rust-proofing properties. It is suitable for an effective protection against corrosion in vehicle body cavities and convinces with very good application properties and final performance. Thanks to its very high creep capability, it well protects even hardly accessible areas and tight sheet intervals. After drying, a brown, slightly sticky wax coating remains that protects cavity areas from corrosion.

**PRODUCT BENEFITS**

- Shake and Spray - equipment independent (aerosol)
- Very good creep capability making easy application even at colder temperatures
- Excellent film building properties
- Outstanding water displacing
- Easy to use
- Road salt resistant
- Permanently elastic
- Heat resistant

**AREAS OF APPLICATION**

Sikagard®-6220 S is a spray applied anti-corrosion coating for repair and protection of open cavities and concealed areas of vehicles such as cavities of door skins, side panels, motor hoods, trunks, rear wing, sills, cross members and pillars.

The product penetrates finest hairline cracks but does not drip through drainage holes.

Sikagard®-6220 S shows very good adhesion on different paints, metal primers, metals and PVC without any pre-treatment.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

## CHEMICAL RESISTANCE

Sikagard®-6220 S is resistant against water, seawater, salt spray, oil, soft bases and acids. The above information is offered for general guidance only. Advice on specific applications will be given on request.

## METHOD OF APPLICATION

### Surface preparation

Surfaces must be clean, dry and free of rust, dust and grease. Bare metal must be pre-treated to enhance corrosion resistance (e.g. uncoated steel, etc).

### Application

Shake can approx. 40 times before use. Cover adjacent surfaces prior the spray process. Hold the can in an upright position, spray at room temperature and from a distance of approx. 25 cm on the surface or in the cavities. To reach cavities use the additional actuator with flexible hose. Use the existing or drill access points in the car body.

Spray a continuous coat. Do not spray on parts of the brake, engine or exhaust system. After use, invert can and spray in short bursts to clear nozzle.

Due to the flammable propellant ventilate the cavities during the drying time or before closing the cavities.

## Removal

Uncured Sikagard®-6220 S can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once dried, the material can only be removed mechanically. Hands and exposed skin shall be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin.

## Overpainting

Sikagard®-6220 S cannot be overpainted.

## FURTHER INFORMATION

Copies of the following publication is available on request:

- Safety Data Sheet

## PACKAGING INFORMATION

Aerosol can	500 ml
-------------	--------

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

## PRODUCT DATA SHEET

Sikagard®-6220 S  
Version 01.01 (08 - 2024), en\_ET  
015113022203001100

## SIKA ABYSSINIA

Chemicals Manufacturing PLC  
Sebeta, Welete · Addis Ababa  
ETHIOPIA  
Phone: +251.113.679.748  
Web: eth.sika.com

